

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau

(43) International Publication Date
7 March 2002 (07.03.2002)

PCT

(10) International Publication Number
WO 02/17886 A1(51) International Patent Classification: A61K 9/48, C08J
5/18, C08L 5/06, 3/08, 89/06

(21) International Application Number: PCT/EP01/09594


(22) International Filing Date: 21 August 2001 (21.08.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
00402423.8 1 September 2000 (01.09.2000) EP(71) Applicant (for all designated States except US):
WARNER-LAMBERT COMPANY [US/US]; 201
Tabor Road, Morris Plains, NJ 07950 (US).(72) Inventors; and
(75) Inventors/Applicants (for US only): SCOTT, Robert
[GB/BE]; Königin Elisabethplein 26, bus 4, B-9100
Sint Niklaas (BE). CADE, Dominique [FR/FR]; 11, rue
des Américains, F-68000 Colmar (FR). HE, Xiongwei
[CN/FR]; 3, rue du Jura, F-68280 Andolsheim (FR).(74) Agents: MANSMANN, Ivo et al.; Gödecke GmbH,
Patents, Mooswaldallee 1, 79090 Freiburg (DE).(81) Designated States (national): AE, AG, AL, AU, BA, BB,
BG, BR, BZ, CA, CN, CO, CR, CU, CZ, DM, DZ, EC, EE,
GD, GE, HR, HU, ID, IL, IN, IS, JP, KP, KR, LC, LK, LR,
LT, LV, MA, MG, MK, MN, MX, NO, NZ, PH, PL, RO,
SG, SI, SK, TT, UA, US, UZ, VN, YU, ZA.(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD,
TG).Declaration under Rule 4.17:
— of inventorship (Rule 4.17(iv)) for US onlyPublished:
— with international search report
— before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendmentsFor two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PECTIN FILM COMPOSITIONS



(57) Abstract: The invention concerns film-forming compositions containing pectin, at least one additional film-forming polymer and a setting system for use in pharmaceutical, veterinary, food, cosmetic or other products like films for wrapping food, aspics or jellies, preferably for predosed formulations like soft or hard capsules, as well as aqueous solutions of the compositions for the manufacturing of said products.

WO 02/17886 A1

WO 02/17886

PCT/EP01/09594

1

Pectin Film Compositions

The invention concerns film compositions containing pectin, at least one additional film-forming polymer and a setting system for use in pharmaceutical, veterinary, food, cosmetic or other products like films for wrapping food, aspics or jellies, preferably for predosed formulations like soft or hard capsules.

Preferably pectin compositions are used for manufacturing of hard capsules for pharmaceutical and veterinary applications. The pectin content of the compositions confers enteric properties to such capsules and at least one further film-forming polymer enhances the mechanical performance of the hard capsules. Combination with a setting system allows use of the film-forming compositions of the invention for industrial enteric capsule production by conventional dip moulding processes.

The use of conventional dip moulding equipment for gelatin capsule production allows the production of enteric capsules with equal dimensions and properties which can be used with conventional filling equipment for gelatin capsules.

Enteric materials have a pH-dependent solubility. They are insoluble under gastric conditions (simulated by a pH of 1.2) and readily soluble under intestinal conditions (simulated by a pH of 6.8). Generally, these materials are polymers containing carboxylic groups, such as cellulose acetate phthalate (CAP), hydroxypropyl methylcellulose phthalate (HPMCP), hydroxypropyl methylcellulose acetate succinate (HPMC-AS), acrylic copolymers, pectin or alginates.

Usually enteric properties of pharmaceutical compositions are achieved by a coating process with enteric materials on e.g. granules, pellets, tablets or hard or soft capsules.

Enteric film compositions for hard capsules are described for example in US 4,138,013. The film-forming composition for dip moulding consists of (1) hydroxypropyl methylcellulose and an ammonium salt of cellulose acetate phthalate polymer or (2) of gelatin and an ammonium salt of a copolymer of methacrylic acid

WO 02/17886

PCT/EP01/09594

2

and methacrylic acid ester. However, it has been found that capsules made according to the mentioned techniques have the disadvantages of poor solubility in intestinal juice, high organic solvent content, inadequate stability and diffusion problems.

Improvements are described in EP-A-0 056 825 with film compositions containing
5 film-forming polymers like cellulose esters or cellulose ether esters, plasticizers, viscosity-increasing substances like highly viscous cellulose ethers, and anti-foaming agents.

Conventional hard capsules are produced from gelatin by a dip moulding process. This process is based on the setting ability of hot gelatin solution by cooling. On a
10 totally automatic industrial hard gelatin capsule machine, mould pins are dipped into hot gelatin solution, the pins are removed from the solution, inverted, the gelatin solution (gel) remaining on the pins dried, stripped off the capsule shells and finally cap and body of the capsules cut and pre-joined. The immediate setting of the gelatin
15 solution on the mould pins after dipping is the key step in the process. Otherwise, the gelatin solution would flow down to form capsules with non-uniform wall thickness and unacceptable properties.

A further enteric film composition consisting of a mixed ester of an alkyl-,
hydroxyalkyl- or hydroxyalkyl alkylcellulose esterified with succinyl anhydride and
an aliphatic monocarboxylic acid anhydride is described in US 4,365,060. However,
20 the solutions from these compositions do not possess any setting ability and therefore are not applicable to industrial-scale dip moulding processes.

JP-A-58138458 describes a process for dipping mould pins into an aqueous solution of hydroxypropyl-methyl-cellulose acetate succinate alkali metal salt and gelatin and thereafter dipping in aqueous acid solution. However, in this composition the gelatin
25 content is too low to provide sufficient setting ability to the dipping solution.

WO 02/17886

PCT/EP01/09594

3

Surprisingly, we have found that film compositions based on pectin as enteric material with at least a second film-forming material and a setting system have sufficient setting ability for industrial hard capsule production.

5 Pectin has excellent enteric properties. A relatively low content of pectin from 5 to 25 %, preferably 10 to 20 % by weight in the composition, is sufficient to obtain capsule films with enteric properties. Surprisingly, the capsule of the present invention can resist dissolution at least for 2 hours in in-vitro disintegration tests at pH 1.2, and is easily soluble at pH 6.8 (> 80 % after 45 min under USP dissolution conditions).

10 The aqueous solutions of the film-forming compositions of the prior art are necessarily prepared under alkaline conditions and for this reason are quite unstable. This disadvantage is overcome by the compositions of the invention because the pectin used as enteric material is water soluble and consequently, the solution is quite stable.

15 A further advantage of pectin is that pectin itself has the properties of a setting agent as described below.

A disadvantage of pectin is its brittleness like other enteric materials, if it is used in film-forming compositions alone or in high amounts. Surprisingly, we have found that this problem could be solved by the addition of at least one further film-forming material to the film-forming composition, which may be selected generally from all
20 hydrosoluble film-forming materials of pharmaceutical and/or food quality grade. Suitable are for example gelatin; pullulan; polyvinyl alcohol; modified starches such as hydroxypropylated starch or hydroxyethylated starch; cellulose ethers such as hydroxypropyl methylcellulose, hydroxypropyl cellulose, methylcellulose, hydroxyethyl cellulose or hydroxyethyl methylcellulose; and mixtures thereof.

25 Beside the improvement of the mechanical properties of the capsule film the addition of a second film-forming material also increases the content of solid material in the dip mould solution of the film composition.

WO 02/17886

PCT/EP01/09594

4

The content of pectin is in the range of 5 to 60 %, preferably 10 to 40 %, and that of the second film-forming material in the range of 40 to 95 %, preferably 50 to 85% by weight in the film composition.

Low methoxyl pectins (LM pectins) with a degree of esterification of the carboxyl groups with methanol below 50% are especially preferred.

The dipping solution for the capsule manufacturing process has a content of the film-forming composition in the range of 15 to 40 % by weight.

For the production of enteric capsules by an industrial dipping process, it is essential that the dipping solution has a sufficient setting ability. Surprisingly, we have found that pectin, beside its enteric properties, can provide a sufficient setting behavior in the presence of divalent cations such as Ca^{++} or Mg^{++} . The content of the divalent salts such as CaCl_2 in the dipping solution is preferably from 100 ppm to 5000 ppm (0.01 to 0.5 % by weight), this means an amount of from 0.04 to 2 % by weight of the final film composition. During the preparation of the solution, the formation of concentration peaks of the divalent salt has to be avoided. High local concentrations of the divalent salt will result in thermally irreversible local pectin gel formation.

The setting behavior of the film-forming solution of the invention may be also achieved or altered by the addition of further gelling agents, preferably polysaccharides such as carrageenan or gellan. It has been found that addition of a small quantity of such additional gelling agent can provide sufficient setting ability. The gelling agent content in the dipping solution is preferably from 0.05 to 2 % by weight, this means an amount of from 0.2 to 8 % by weight of the final film composition.

The temperature of the solution during the dipping process is also important for the setting properties of the dipping solution. Preferably the temperature should be above 50°C, and is dependent on the pectin content. It has been found that the temperature of the dipping solution has to be increased with higher pectin contents.

WO 02/17886

PCT/EP01/09594

5

The inventive composition may contain in a further aspect additional pharmaceutically or food-acceptable colouring agents in the range of 0 to 10 % based upon the weight of the final film composition.

5 The inventive composition may contain in a further aspect additional pharmaceutically or food acceptable plasticizer or flavouring agents.

Finally, the inventive film-forming solution can be used for banding enteric capsules. This prevents the capsule from leaking or separation of body and cap in gastric fluids.

The following examples and tests illustrate hard enteric capsule production with the composition from the dipping solutions of the invention and its enteric properties.

10 **Example 1**

In 3.9 kg of deionised water at room temperature 2.5 g of CaCl_2 (0.05 % by weight of the final dipping solution) and 100 g of glycerol (plasticizer, 2 %) were dissolved, then 200 g of LM pectin (4 %) and 800 g of hydroxypropyl starch (16 %) dispersed. The mixture was then heated to 95°C to solubilize all components under stirring.
15 After debubbling by reducing the stirring, the solution was equilibrated at 60°C.

The solution was poured into a dipping dish of a pilot machine of conventional hard gelatin capsule production equipment. Keeping the dipping solution at 60°C, natural transparent hard enteric capsules of size 0 were produced according to the conventional process with the same dimensional specifications as the conventional
20 hard gelatin capsules. The final capsules have a film composition of 16.3% pectin, 65.3% hydroxypropyl starch, 8.1% glycerol, 0.20% CaCl_2 and 10% moisture by weight.

Example 2

200 g of LM pectin was dispersed into 2.0 kg of deionised water at room temperature,
25 and then the mixture was heated to 85°C to solubilize the pectin. After debubbling by reducing the stirring, the solution was then equilibrated at 60°C.

WO 02/17886

PCT/EP01/09594

6

2.5 kg of aqueous gelatin solution at 32 % was prepared by conventional method for hard gelatin capsule manufacture. 11.75 g of CaCl_2 aqueous solution at 20 % was added to the gelatin solution, which was then debubbled by standing at 60°C.

5 The above two solutions were mixed together by gentle stirring to avoid creating bubbles. The solution thus prepared (containing 4.25 % pectin, 17.0 % gelatin and 0.05 % CaCl_2 by weight) was then poured into a dipping dish of a pilot machine of conventional hard gelatin capsule production equipment. Keeping the dipping solution at 45°C, natural transparent hard enteric capsules of size 0 were produced according to the conventional process with the same dimension specifications as the

10 conventional hard gelatin capsules.

The final capsules have a film composition of 16.9% pectin, 67.4% gelatin, 0.20% CaCl_2 and 15.5% moisture by weight.

Example 3

250 g of polyethyleneglycol 400, pre-heated at 60°C was added under gentle stirring

15 into 4.7 kg solution at 60°C, containing by weight 4.25 % pectin, 17.0 % gelatin and 0.05 % CaCl_2 , prepared as in example 2.

Natural transparent enteric hard capsules were produced as in example 2. The final capsules have a film composition of 13.9 % pectin, 55.8% gelatin, 17.4% PEG400 and 0.16% CaCl_2 and 12.7% moisture by weight.

20 Example 4

3.85 g of gellan gum and 150 g of LM pectin were dispersed into 2.0 kg of deionised water at room temperature. The mixture was then heated to 85°C for solubilization. After debubbling, the solution was then equilibrated at 60°C.

2.66 kg of aqueous gelatin solution containing 32 % gelatin by weight was prepared

25 by conventional method for hard gelatin capsule manufacturing and equilibrated at 60°C.

The above two solutions were mixed and debubbled. The final solution contained 3.12 % pectin, 17.7 % gelatin and 0.08 % gellan gum by weight.

WO 02/17886

PCT/EP01/09594

7

Natural hard enteric capsules of size 0 were produced in the same manner as in the previous examples, keeping the dipping solution at 55°C. The final capsules have a film composition of 12.8% pectin, 72.4% gelatin and 0.33% gellan gum and 14.5% moisture by weight.

- 5 All the capsules were evaluated for their enteric performance by in-vitro disintegration and dissolution tests according to the UPS XXIII: first 2 hours in simulated gastric fluid (pH1.2) and then in simulated intestinal fluid (pH6.8). No enzyme was used in these tests.

- 10 The capsules were filled with lactose containing 0.1 % of Indigotine (FD&C blue N°2) for disintegration test or filled with acetaminophen for in-vitro dissolution test. Capsules were then banded with the same solution used respectively during the capsule manufacture for each example. The capsule banding prevents separation of capsule cap and body during the disintegration test.

- 15 The results of the disintegration tests are shown in Table 1 and the results of the dissolution tests are shown in Figure 1.

Table 1

Disintegration Results

Capsule	Disintegration time	
	pH1.2	pH6.8
Example 1	>2 h	10.6 min
Example 2	>2 h	3.5 min
Example 3	>2 h	2.5 min
Example 4	>2 h	4.8 min

- 20 The tests performed confirmed the excellent gastric resistance of all capsules, they remained intact even after 2 hours exposition to pH 1.2.

WO 02/17886

PCT/EP01/09594

8

Capsules of examples 1-3 dissolved very quickly after passing into pH 6.8 buffer solution. Capsules of example 4 showed some delay. The use of an additional setting agent would be a possibility to modulate the dissolution profile under intestinal conditions.

WO 02/17886

PCT/EP01/09594

9

Claims

1. Film composition comprising
 - a) pectin,
 - b) a second film-forming polymer and
 - c) a setting system.
2. Film composition according to claim 1, wherein the second film-forming polymer is selected from gelatin; pulhulan; polyvinyl alcohol; hydroxypropylated starch, hydroxyethylated starch; hydroxypropyl methylcellulose, hydroxypropyl cellulose, methyl cellulose, hydroxyethyl cellulose, hydroxyethyl methylcellulose; or mixtures thereof.
3. Film composition according to claim 1 wherein the content of pectin is from 5 to 50 %, preferably 10 to 40 %, and that of the second polymer from 60 to 95 %, preferably 50 to 85%.
4. Film composition according to claim 1 wherein the setting system consists of pectin and divalent cation salts.
5. Film composition according to claim 4 wherein the divalent cation salts are selected from magnesium or calcium salts.
6. Film composition according to claim 1 wherein the setting system consists of pectin and an additional setting agent selected from carrageenan or gellan gum or mixtures thereof.
7. Film composition according to claim 1 wherein additionally colouring agents and/or flavouring agents are contained.
8. Film composition according to claim 1 wherein additionally plasticizers are contained.

WO 02/17886

PCT/EP01/09594

10


9. Film-forming aqueous solution of the composition according to claim 1 for the manufacture of hard enteric capsule.
10. Solution according to claim 9 containing the film-forming composition of claim 1 in an amount of 10 to 50 %, preferably 15 to 40 % by weight of the aqueous solution.
11. Solution according to claim 9 containing the salt of a divalent cation in an amount of 0.01 to 0.5 % by weight of the aqueous solution.
12. Solution according to claim 11 characterized in that the salt of a divalent cation is a magnesium and/or calcium salt.
13. Aqueous solution according to claim 9 containing an additional setting agent selected from carrageenan and/or gellan gum, in an amount of 0.05 to 2 % by weight of the aqueous solution.
14. Use of the aqueous solution according to claim 9 for the manufacture of hard enteric capsules by a dip moulding process.
15. Manufacturing of hard enteric capsules from an aqueous solution containing 10 to 50 % by weight of the film-forming composition of claim 1 by a dip moulding process with conventional hard gelatin capsule production equipment at temperatures between 40 and 70°C.
16. Use of the aqueous solution according to claim 9 for the banding process of enteric capsules.

WO 02/17886

PCT/EP01/09594

1/1

FIG. 1



INTERNATIONAL SEARCH REPORT

 Intern: Application No
 PCT/EP 01/09594

 A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 A61K9/48 C08J5/18 C08L5/06 C08L3/08 C08L89/06

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

 Minimum documentation searched (classification system followed by classification symbols)
 IPC 7 A61K C08J C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 16, no. 190 (C-937), 8 May 1992 (1992-05-08) & JP 04 027352 A (FUJI KAPUSERU KK), 30 October 1992 (1992-10-30) abstract & DATABASE WPI Week 1992 Derwent Publications Ltd., London, GB; AN 1992-084752 abstract	1-16

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

9 January 2002

Date of mailing of the international search report

22/01/2002

Name and mailing address of the ISA

 European Patent Office, P.B. 6818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 840-2040, Tx. 31 651 epo nl,
 Fax (+31-70) 340-8016

Authorized officer

Lensen, H

Form PCT/ISA/210 (second sheet) (July 1992)

page 1 of 2

ENSDOCID: <WO 021788A1_L>

INTERNATIONAL SEARCH REPORT

Intern. Application No.
PCT/EP 01/09594

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 16, no. 207 (C-941), 18 May 1992 (1992-05-18) & JP 04 036159 A (FUJI KAPUSERU KK), 6 February 1992 (1992-02-06) abstract & CHEMICAL ABSTRACTS, vol. 116, no. 23, 8 June 1992 (1992-06-08) Columbus, Ohio, US; abstract no. 234272, FUKAZAWA TAKAYUKI ET AL.: "Soft capsules containing royal jelly-cyclodextrin complex." abstract	1-16
X	PATENT ABSTRACTS OF JAPAN vol. 8, no. 3 (C-203), 7 October 1984 (1984-10-07) & JP 58 172313 A (MORISHITA JINTAN), 11 October 1983 (1983-10-11) abstract & DATABASE WPI Week 198346 Derwent Publications Ltd., London, GB; AN 1983-818130 abstract	1-16
X	US 5 431 917 A (TAIZO YAMAMOTO ET AL.) 11 July 1995 (1995-07-11) column 2, line 25 -column 4, line 33	1,2,4,5, 7,9,14, 15
X	WO 00 18835 A (WARNER-LAMBERT COMPANY) 6 April 2000 (2000-04-06) page 2, line 21 -page 6, line 8	1-5,8
A	GB 1 559 644 A (SUMITOMO CHEMICAL COMPANY) 23 January 1980 (1980-01-23) page 2, line 28 - line 30	
A	EP 0 888 778 A (SAMYANG CORPORATION) 7 January 1999 (1999-01-07) page 5, line 51 - line 52	

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

page 2 of 2

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. Application No.

PCT/EP 01/09594

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
JP 04027352	A	30-01-1992	NONE	
JP 04036159	A	06-02-1992	NONE	
JP 58172313	A	11-10-1983	NONE	
US 5431917	A	11-07-1995	US 5264223 A	23-11-1993
WO 0018835	A	06-04-2000	FR 2783832 A1	31-03-2000
			AU 5347299 A	17-04-2000
			CN 1321177 T	07-11-2001
			EP 1117736 A1	25-07-2001
			WO 0018835 A1	06-04-2000
GB 1559644	A	23-01-1980	JP 53026867 A	13-03-1978
			DE 2737947 A1	02-03-1978
			FR 2362888 A1	24-03-1978
EP 888778	A	07-01-1999	KR 219918 B1	01-09-1999
			AU 4400797 A	25-01-1999
			EP 0888778 A1	07-01-1999
			JP 2001509471 T	24-07-2001
			WO 9901115 A1	14-01-1999
			US 6319518 B1	20-11-2001

Form PCT/ISA/210 (patent family annex) (July 1992)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☒ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.